Rec'd PCTAPTO 14 OCT 2014

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



1 CORTO ANTOCOM DE CORTO ACORDO COM LA PORTE CORTO ACORDO DE CORTO DE CONTROL DE CONTROL DE CORTO DE CORTO DE

(43) International Publication Date 6 November 2003 (06.11.2003)

PCT

(10) International Publication Number WO 03/090988 A1

- (51) International Patent Classification?: B28B 21/18, 7/30
- (21) International Application Number: PCI/AU03/00481
- (22) International Filing Date: 24 April 2003 (24.04.2003)
- (25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: PS 1953


26 April 2002 (26.04.2002) AU

- (71) Applicant (for all designated States except US): VERTECH HUME PTY LTD [AU/AU]; 64 Lock Avenue, Warribee, VIC 3030 (AU).
- (72) Inventor; and
- (75) Inventor/Applicant (for US only): HUME, Graeme, Reginald [AU/AU]; 64 Lock Avenue, Werribee, VIC 3030 (AU).

- (74) Agent: MISCHLEWSKI, Darryl; I P Strategies, P.O. Box 1254, Camberwell, VIC 3124 (AU).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: VERTICAL MOULDING OF CONCRETE



WO 03/090988 A1

(57) Abstract: A method of moulding long concrete articles in a vertical mould which incorporates a mould liner (17) with drainage tubes (5) used to dewater the concrete when the mould is filled. The improvement is to close off the drainage tubes (5) during the filling of the mould to inhibit water loss in the concrete during filling. The drainage tubes (5) may incorporate one way valves or include inner tubes (15) that may be pressurized to inhibit water entering the drainage tube (5).

BEST AVAILABLE COPY